

Terpolymer	Propylene Content (% wt)	Viscosity Mooney ML (1+4) 125°C	Oil Content (% wt)	ENB (%)
DUTRAL® TER 4033	25	30	-	5
DUTRAL® K TER 4033	25	30	-	5
DUTRAL® TER 4038 EP	27	60	-	4.4
DUTRAL® TER 4039	27	77	-	4.4
DUTRAL® TER 4044	35	44	-	4
DUTRAL® TER 4047	40	55	-	4.5
DUTRAL® TER 4049	40	76	-	4.5
DUTRAL® TER 7040	40	87	-	6.5
DUTRAL® TER 4334	27	28	30	4.7
DUTRAL® TER 4436	28	43	40	5.5
DUTRAL® TER 4437	32	57	40	4.5
DUTRAL® TER 4437 WO	32	57	40	4.5
DUTRAL® TER 4535	32	32	50	3.4
DUTRAL® TER 4548	36	47	50	4.5
DUTRAL® TER 6537	32	43	50	8
DUTRAL® TER 9046	31	67	-	8.9