

	ASTM	MT N-990	MT N-991	N-772
Appearance		Pellets	Powder	Pellets
Adsorption DBP (ml/100g)	D 2414	40	40	65
Iodine no. (mg/g)	D 1510	8	8	29
Ph value	D 1512	9	9	
Ash (% max.)	D 1506	0,1	0,1	0,4
Sieve residue (325 mesh, ppm)	D 1514	27	34	200
Bulk density (kg/m ²)	D 1513	500	360	420