

<b>Emulsion Styrene Butadiene Rubber (SBR)</b>	<b>Grade</b>	<b>Styrene (%)</b>	<b>Viscosity ML (1+4) 100°C</b>	<b>Oil Content phr</b>
E-SBR	1500	23,5	52	-
E-SBR	1502	23,5	52	-
E-SBR	1502 F	23,5	52	-
E-SBR	1509	23,5	33	-
E-SBR	1721	40	54	37,5 DAE
E-SBR	1723	23,5	48	37,5 TDAE
E-SBR	1739	40	52	37,5 TDAE
E-SBR	1778	23,5	49	37,5 NAPH
HSR	HS 630	63	56	-