

## LUVOMAXX BC Carcass grades

	<b>ASTM</b>	<b>N-550</b>	<b>N-550 LG*</b>	<b>N-650</b>	<b>N-660</b>	<b>N-762**</b>	<b>N-772</b>
Appearance		Pellets	Pellets	Pellets	Pellets	Pellets	Pellets
Adsorption DBP (ml/100g)	D 2414	121	121	122	90	65	65
Iodine no. (mg/g)	D 1510	43	43	36	36	27	30
Ash (% max.)	D 1506	0,5	0,5	0,5	0,5	0,5	0,75
Volatiles (% max.)	D 1514	1,5	1,0	1,5	1,5	1,5	1,0
Bulk density (kg/m <sup>2</sup> )	D 1513	350	360	360	420	374	500