

NBR-PVC	ACN (%)	Viscosity Mooney ML (1+4) 100°C
EUOPRENE N OZO 7028	19,5	75
EUOPRENE N OZO 7028/60	19,5	60
EUOPRENE N OZO 7033	23	75
EUOPRENE N OZO 7033/60	23	60
EUOPRENE N OZO 7039	27	75
EUOPRENE N OZO 7045	31,5	95
EUOPRENE N OZO 5033	16,5	70