

<b>Polyisoprene (IR)</b>	<b>Tg</b>	<b>Viscosity Mooney ML (1+4) 100°C</b>
ISOGRIP (60% 3,4 - IR)	-11°C	70