

<b>Copolymere</b>	<b>Propylene Content (% wt)</b>	<b>Viscosité Mooney ML (1+4) 125°C</b>	<b>Huile (% wt)</b>
DUTRAL CO 034	28	44	-
DUTRAL CO 038	28	60	-
DUTRAL CO 043	45	33	-
DUTRAL CO 054	41	44	-
DUTRAL CO 058	48	80	-
DUTRAL CO 059	41	79	-