

| Carboxylated Styrene Butadiene Latex | Styrene (%) | Brookfield Viscosity (20 rpm, 25°C, mPa.s) |
|---|--------------------|---|
| EUROPRENE® Latice 405 | 40 | 300 |
| EUROPRENE® Latice 406 | 40 | 300 |
| EUROPRENE® Latice 440 | 60 | 300 |
| EUROPRENE® Latice 455 | 47 | 300 |
| EUROPRENE® Latice 5583 | 40 | 300 |
| EUROPRENE® Latice 5584 | 60 | 400 |
| EUROPRENE® Latice 5585 | 47 | 300 |
| EUROPRENE® Latice 5587 | 75 | 600 |
| EUROPRENE® Latice 5588 | 50 | 350 |
| EUROPRENE® Latice 8435 | 69 | 600 |
| EUROPRENE® Latice 8487 | 67 | 500 |